

Stratigraphy

- 1 PE film
- 2 Waterproofing mass
- 3 Single strand composite polyester reinforcement
- 4 Waterproofing mass
- 5a Polypropylene mat finish
- 5b Mineral finish

Characteristics

ELASTO PRO is a prefabricated membrane made of bitumen distillate modified with special polymers

(SAP), reinforced with spunbond non-woven polyester filaments.

The waterproofing compound obtained through the complete homogenization of bitumen distillate with SAP polymers is added with special additives, and offers excellent features:

- resistance to U.V. radiation
- resistance to temperature change
- resistance to O3
- resistance to chemical corrosion (acids and salts)
- waterproof seal

Finishing

The upper face of ELASTO PRO P is finished with a polypropylene mat.

ELASTO PRO PA instead have their upper face protected with granules of white slate which in addition to offering an aesthetical finish provides protection against UV radiation and heat in this way preserving the roof covering from aging.

10 cm wide selvedge has been left at the side to improve overlapping of rolls.

The lower face is protected by a groove embossing with PE film.

The latter has the function of optimizing and maximizing adhesion of the membrane to the laying surface during hot application: respect at a traditional embossing, the surface is more uniform.

The thousand lines per square meter operate a uniform marking and close-up of the PE film thus ensuring a homogeneous opening in the phase of application, obtaining the maximum adhesion to the application plan.

Groove embossing facilitates the operator during the flaming because it requires less flame intensity and therefore less absorption of heat from the product itself, eliminating the problems of "Footprints" that occur on the upper face of the both smooth and slated products.

Methods of application

- The membrane is usually applied by heating the bituminous blend using a gas burner or hot air guns in special cases.
- Always use the individual protection devices specified by law.
- Never use application by heating on heat-sensitive supports or insulation.
- Conduct regular maintenance on the roof in order to remove detritus, mud, grass, etc., and to keep the operation of the waterproofing system and accessories (drains, TV antennas, air-conditioning systems, etc.) under control.
- Whenever there is reason to believe that the element to be waterproofed has traces of residual humidity (e.g. during renovations of existing roof coverings, applications after abundant rainfall), vents should be positioned in such way as to permit its elimination.

For more information and instructions, we recommend consulting LARIBIT application manual, remembering that our Technical Support Service is always at your disposal to solve particular problems and provide the assistance necessary in using our waterproofing membranes to best advantage.

Technical data sheet
PROFESSIONAL membranes

Fields of use



EN13707 Continuous roofs (Certificate n° 0958-CPR-2045/1)

	N° LAYERS			METHOD OF APPLICATION					TYPE OF APPLICATION			TYPE					
	Single Layer	Double Layer	Multilayer	Torch	Hot Air	Mixed (Torch / Air)	Cold Bond Glue	Mechanical Fixing	Thermo Adhesive / Self Adhesive	Fully Bonded	Partially Bonded	Loose Laid	Complimentary Layer	Top Layer	Heavy Protection	Anti-root	Other Uses
ELASTO PRO P 4 MM		•	•	•						•				•			
ELASTO PRO PA 4.5 KG/M²		•	•	•						•				•			





EN13859-1 Under roof tile

ELASTO PRO PA 4.5 KG/M²	•	•	•	•						•				•			
--------------------------------	---	---	---	---	--	--	--	--	--	---	--	--	--	---	--	--	--

The waterproofing membrane based on distilled bitumen and polymers, as shown in this data sheet does not require the issue of a MSDS, because it does not contain dangerous substances. The information data sheet for the proper use of products is available.

Application

- On cementitious surfaces and similar apply, by roller or airless, bituminous primer, approx. consumption 300/400 g/m².
- Apply by torch application a 25 cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point. (Draw. N.1)
- Position the membrane sheets staggered, avoiding to create any overlaps against the slope and the drains. (Draw. N.2)
- Cut the corners of membrane sheet which will be laid under the next sheet at a 45° angle (10 x 10 cm). (Draw. N.3)
- The joints, both side and head, must be respectively overlapped by 10 & 15 cm. (Draw. N.3)
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet. (Draw. N.4)
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10 cm) and head laps (15 cm) will be heat welded with an appropriate torch; during this stage the overlaps should be pressed by using a roller (15 kg) from which a bead of compound should flow and therefore avoiding to have to iron the overlaps.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10 cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15 cm.



Elasto Pro

Recommendations

- The rolls are to be stored in an upright position, indoors in a dry and ventilated area, away from heat sources. Absolutely avoid the stacking of rolls and pallets for storage or transport to avoid possible deformations which may compromise a perfect installation. It is recommended to store the product at temperatures above 0°C.
- The application surface must be smooth, dry, and clean.
- The application surface must be previously treated with the appropriate bituminous primer.
- **The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.**
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The product must be applied at room temperatures of above + 5°C.
- Application must be suspended during inclement weather (excessive humidity, rain, etc.).
- The materials without mineral self-protection or dual reinforcement, used as a top layer (cap sheet), can be painted with an aluminium coating to improve and extend the performance and life expectancy, the material should be allowed to oxidize approx. 3-6 months before being coated. An alternative, depending on the type of construction, it is possible to use heavy protection (floating pavements, stone, etc.).
- The pallets supplied are suited only for normal warehouse movement and not for raising heavy loads to height.
- We recommend making correct and regular warehouse rotation.
- For information concerning storage and application of Laribit membranes, please refer to the "Installation manual".

Technical data

Technical Characteristics	Measure Units	Reference Norm	P	PA	Tolerance
Type of reinforcement			Single strand polyester		
Upper face finish			Polypropylene mat	Mineral *	
Lower face finish			PE film		
Watertightness	kPa	EN 1928	60		
Length	m	EN 1848-1	10 -1%		
Width	m	EN 1848-1	1 -1%		
Thickness	mm	EN 1849-1	4		±5%
Mass	kg/m ²	EN 1849-1		4,5	±10%
Cold flexibility	°C	EN 1109	-15		
Flow resistance	°C	EN 1110	110		
Flow resistance after ageing	°C	EN 1296		110	-10°C
Shear resistance L / T	N / 5 cm	EN 12317-1	500/400		
Tensile strength L / T	N / 5 cm	EN 12311-1	600/500		
Elongation at break L / T	%	EN 12311-1	40/40		
Tearing resistance L / T	N	EN 12310-1	150/150		
Static puncture resistance	kg	EN 12730	15		
Dynamic puncture resistance	mm	EN 12691	1000		
Dimensional stability	%	EN 1107-1	-0,5		
Loss mineral	%	EN 12039		30	
Fire resistance		EN 13501-5	F ROOF		
Fire reaction		EN 13501-1	F		

* Mineral self-protected products may undergo color tone variations due to the time and length of storage. Exposure to atmospheric conditions, after application, will tend to uniform the color after a few months. The change in color tone cannot therefore be contested and / or complained of as it is a natural phenomenon that the slate manufacturer himself cannot guarantee.

Sizes & packing

	P 4 mm	PA 4,5 kg/m ²
Rolls size [m]	10x1	10x1
Rolls per pallet	25	25
Square meters per pallet [m ²]	250	250

Sizes & packing may vary depending on the type of transportation. The technical data given is based on average values obtained during production. We reserve the rights to change or modify the nominal values without prior notice or advice. The information contained in this data sheet are based on our experience. We cannot take any responsibility for a possible incorrect use of the products. The customer has to choose under their own responsibility a product fit for the intended use.

Laribit®

Matco S.r.l. - Via Quadrelli 69
37055 Ronco all'Adige (VR) Italy

Tel. +39 045 8775559 www.laribit.com
Fax +39 045 8751474 info@laribit.com

CE