

Application

- On cementitious surfaces and similar apply, by roller or airless, bituminous primer, approx. consumption 300/400 g/m².
- Apply by torch application a 25 cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point. (Draw. N.1)
- Position the membrane sheets staggered, avoiding to create any overlaps against the slope and the drains. (Draw. N.2)
- Cut the corners of membrane sheet which will be laid under the next sheet at a 45° angle (10 x 10 cm). (Draw. N.3)
- The joints, both side and head, must be respectively overlapped by 10 & 15 cm. (Draw. N.3)
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet. (Draw. N.4)
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10 cm) and head laps (15 cm) will be heat welded with an appropriate torch; during this stage the overlaps should be pressed by using a roller (15 kg) from which a bead of compound should flow and therefore avoiding to have to iron the overlaps.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10 cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15 cm.



MT P+V

Recommendations

- The rolls are to be stored in an upright position, indoors in a dry and ventilated area, away from heat sources. Absolutely avoid the stacking of rolls and pallets for storage or transport to avoid possible deformations which may compromise a perfect installation. It is recommended to store the product at temperatures above 0°C.
- The application surface must be smooth, dry, and clean.
- The application surface must be previously treated with the appropriate bituminous primer.
- **The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.**
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The product must be applied at room temperatures of above + 5°C.
- Application must be suspended during inclement weather (excessive humidity, rain, etc.).
- The materials without mineral self-protection or dual reinforcement, used as a top layer (cap sheet), can be painted with an aluminium coating to improve and extend the performance and life expectancy, the material should be allowed to oxidize approx. 3-6 months before being coated. An alternative, depending on the type of construction, it is possible to use heavy protection (floating pavements, stone, etc.).
- The pallets supplied are suited only for normal warehouse movement and not for raising heavy loads to height.
- We recommend making correct and regular warehouse rotation.
- For information concerning storage and application of Laribit membranes, please refer to the "Installation manual".

Technical data

Technical Characteristics	Measure Units	Reference Norm	P+V	Tolerance
Type of reinforcement			Polyester + Fibre glass	
Upper face finish			Sand	
Lower face finish			PE film	
Watertightness	kPa	EN 1928	60	
Length	m	EN 1848-1	8 -1%	
Width	m	EN 1848-1	1,1 -1%	
Thickness	mm	EN 1849-1	4	±5%
Cold flexibility	°C	EN 1109	-10	
Flow resistance	°C	EN 1110	120	
Flow resistance after ageing	°C	EN 1296	110	-10°C
Artificial U.V. ageing		EN 1297	pass	
Tensile strength L / T	N / 5 cm	EN 12311-1	450/400	-20%
Elongation at break L / T	%	EN 12311-1	35/35	-15
Tearing resistance L / T	N	EN 12310-1	130/130	-30%
Dimensional stability	%	EN 1107-1	-0,1	
Fire resistance		EN 13501-5	F ROOF	
Fire reaction		EN 13501-1	F	

Sizes & packing

	P+V 4 mm
Rolls size [m]	8x1,1
Rolls per pallet	30
Square meters per pallet [m ²]	264

Sizes & packing may vary depending on the type of transportation. The technical data given is based on average values obtained during production. We reserve the rights to change or modify the nominal values without prior notice or advice. The information contained in this data sheet are based on our experience. We cannot take any responsibility for a possible incorrect use of the products. The customer has to choose under their own responsibility a product fit for the intended use.

Laribit®

Matco S.r.l. - Via Quadrelli 69
37055 Ronco all'Adige (VR) Italy

Tel. +39 045 8775559 www.laribit.com
Fax +39 045 8751474 info@laribit.com

CE